

Datasheet



22.2V 2900mAh Li-Ion Battery Pack

Salient Features

Description	22.2V 2900mAh
Chemistry:	Lithium Iron Rechargeable Battery
Part No.:	22229
Nominal Voltage	22.2 Volts
Rated Capacity	2900mAh
Length	112 mm
Width	68 mm
Height	40 mm
Typical Weight	350gram
Max. Discharge	30A
Max Charging Current	3 A
Charging	Regulated DC, CCCV 25.2V
Standard Charging	-10 to +45°C
Discharge	-10 to +45°C
Storage	-10 to +45°C
Self-Discharge:	<2% Per month
Cycle Life	> 800 Cycles
Protection Circuit	Euclion.6S PCM protection
Connecters	Standard

- Pack over voltage protection.
- Pack under voltage protection.
- Cell over voltage protection.
- Cell under voltage protection.
- Over load/over current at discharge protection.
- Over current protection at charge.
- Short circuit protection.
- Reverse polarity protection at output.



Table of Contents

1. Scope	3
2. Battery configuration	3
2.1 Model	3
2.2 Assembly Style.....	3
3. Specification	3
3.1 Pack Specification	3
4 General Performance	5
4.1 Common Performance	5
4.2 Safety Performance	6
4.3 Safe Characteristic.....	7
5. Storage and Shipment Requirements	8
6. CAUTIONS IN USE	8
7. Battery operation instruction	9
7.1 Charging	9
7.2 Discharging current	9
7.3 Discharge temperature	9
2.6.1 Over-discharges	9
7.5 Storing the Batteries	9
8. Period of Warranty	10
9. Other- The Chemical Reaction	10
10. Note	10

1. Scope

This specification is applied to the Euclion Energy Pvt Ltd. production of lithium ion rechargeable battery packs.

2. Battery configuration

2.1 Model

Model : 18650/22.2V/2900mAh

2.2 Assembly Style

Assembly Style : 6S1P

3. Specification

3.1 Pack Specification

No.	Items	Criteria	Remarks
3.1	Typical Capacity	2900mAh	Cut off voltage: 17V
	Minimum Capacity	2850mAh	
3.2	Energy	64.38Wh	
1.3	Nominal Voltage	22.2 V	
3.4	Open Circuit Voltage	22.2V to 25V	
3.5	Internal Impedance	Battery : $\leq 3m\Omega$	AC 1KHz after standard charge
3.6	Charge voltage	25.2V	
3.7	Standard charge current	3 A	1C

1.3	Standard discharge current	3A	1C
3.10	Max. discharge current	30 A	10C
3.2.6	Discharge cut-off voltage	17V	
3.12	Operating Temperature	0~+45°C	Charging
		-10~+45°C	Discharging
3.13	Storage Temperature	-20°C~+40°C	Less than 1 month
		-20°C~+30°C	Less than 6 months
3.14	Weight	350gram	

4 General Performance

4.1 Common Performance

No.	Items	Testing method and determinant standard
1	Charge Performance	The battery can be charged when using the original charger. The standard charge mode under the temperature of 23±5°C, charge the battery with the current of 1C until the voltage reaches up to 25.2V, then charge with constant voltage until the charge current ≤ 1C , then stop charging
2	Discharge Performance	When connecting with load, the battery can supply power. Charge the battery with standard charge mode, then rest for 0.5h, then discharge with 1C until the voltage is 17V, and the discharge time is required ≥1 Hours

3	Cycle Performance	Under the temperature of $23\pm 5^{\circ}\text{C}$ charge the battery with .1C, when the voltage reaches up to 25.2V charge with constant voltage until the charge current $\leq 20\text{mA}$, then stop charging, then rest for 2h, then discharge with 1C to 17V. Cycle with the above mode, the test shall be terminated when Discharging Capacity $< 80\%$ of Initial Capacity in three consecutive cycles. The cycle life is required ≥ 800 times.
4	Charged Storage Characteristics	Charge the battery with 1C, then shift to charge with constant voltage until the voltage reaches up to 25.2V, when the charge current $\leq 1\text{C}$ stop charging, rest under the temperature of $23\pm 5^{\circ}\text{C}$ then discharge with 1C to 17V. The discharge time is required 1 Hours.

5	Storage Characteristics		Charge the battery, which is new manufactured shorter than 3 months, with 1C until the capacity reaches to 40~50%, after resting for 6 months under the temperature of $23\pm 5^{\circ}\text{C}$ and the humidity of 45~75%, then charge with 1C to 25.2V then shift to charge with constant voltage, after full-charge rest for 0.5h, then discharge to 17V. The discharge time is required ≥ 1 Hours.	
6	Temperature Dependence of Capacity	35 $^{\circ}\text{C}$ ~45 $^{\circ}\text{C}$	$\geq 90\%$	Charge: 1C, CC/CV, 22.2V, current $\leq 1\text{C}$ cut-off. $23\pm 5^{\circ}\text{C}$ Discharge: at setting temperature 1C, CC, 17V cutoff (Interval for temperature change is 2 hours)
20 $^{\circ}\text{C}$ ~35 $^{\circ}\text{C}$		$\geq 100\%$		
-10 $^{\circ}\text{C}$ ~20 $^{\circ}\text{C}$		$\geq 90\%$		

4.2 Safety Performance

No.	Items	Testing method and determinant standard
1	High Temperature Characteristics	Under the temperature of $23\pm 5^{\circ}\text{C}$, after charging the battery with 1C, then put the battery into the constant temperature and humidity oven with $55\pm 2^{\circ}\text{C}$, then discharge to 17V. The discharge time is required ≥ 1 Hours and the battery should no deformation and smoking.

2	Low Temperature Characteristics	Under the temperature of $23\pm 5^{\circ}\text{C}$ after charging the battery with 1C, then put the battery into the constant temperature and humidity oven with $-10\pm 2^{\circ}\text{C}$ or 16~24h, then discharge with 1C to 17V. The discharge time is required ≥ 1 Hours and the battery should no deformation and smoking.
---	---------------------------------	--

3	Constant Humidity and Temperature Characteristics	Under the temperature of $23\pm 5^{\circ}\text{C}$ after charging the battery with 1C, then put the battery into the constant temperature and humidity oven with $55\pm 2^{\circ}\text{C}$ and 90 ~ 95% for 12h, the battery should be no obvious deformation, leakage, rust, smoking and explosion. After testing take out the battery then rest for 2h under the temperature of $23\pm 5^{\circ}\text{C}$ discharge with 1C to 17V. The discharge time is required ≥ 1 Hours.
---	---	--

4	Drop Test	Under the temperature of $23\pm 5^{\circ}\text{C}$ after full-charging the battery with 1C, then drop it freely from 1.2 meter height onto the hard 18~20mm board. The battery should be no fire and explosion, a After test discharge the battery with 1C, and the discharge time is required ≥ 1 Hours (The battery should be cycled no more than 3 times, among them if one time is passed then stop.).
---	-----------	---

4.3 Safe Characteristic

No.	Item	Test Methods and Condition	Criteria
1	Over charge testing	PCM Protection	No fire or explosion
2	Over discharge testing	PCM Protection.	No explosion, no fire, no leakage.
3	Short-circuit testing	PCM Protection.	No fire or explosion, no leakage.

5. Storage and Shipment Requirements

Item		Requirement
Storage temperature	Short period less than 1 month	-10°C~+45°C
	Long period less than 3 month	23±5°C
Humidity	65±20%RH	
Voltage	22.2-25.2V	

6. CAUTIONS IN USE

To ensure proper use of the battery please read the manual carefully before using it handling.

- Do not expose to, dispose of the battery in fire.
- Do not put the battery in a charger or equipment with wrong terminals connected.
- Avoid shorting the battery
- Avoid excessive physical shock or vibration.
- Do not disassemble or deform the battery.
- Do not immerse in water.
- Do not use the battery mixed with other different make, type, or model batteries.
- Keep out of the reach of children.
-

Charge and discharge

- Battery must be charged in appropriate charger only.
- Never use a modified or damaged charger.
- Do not leave battery in charger over 24 hours.

Storage

- Store the battery in a cool, dry and well-ventilated area.

Disposal

- Regulations vary for different countries. Dispose of in accordance with local regulations.

7. Battery operation instruction

7.1 Charging

Charging current cannot surpass the biggest charging current which in this specification book stipulated.

Charging voltage does not have to surpass the highest amount which in this specification book stipulated to decide the voltage.

Charge temperature: The battery must carry on the charge in the ambient temperature scope which this specification book stipulated uses the constant electric current and the constant voltage way charge, the prohibition reverse charges. If the battery positive electrode and the cathode meet instead, can damage the battery.

7.2 Discharging current

The discharging current does not have to surpass this specification book stipulation the biggest discharging current, the oversized electric current electric discharge can cause the battery capacity play to reduce and to cause the battery heat.

7.3 Discharge temperature

The battery discharge must carry on in the ambient temperature scope which this specification book stipulated

2.6.1 Over-discharges

After the short time excessively discharges charges immediately cannot affect the use, but the long time excessively discharges can cause the battery the performance, battery function losing. The battery long-term has not used, has the possibility to be able to be at because of its automatic flashover characteristic certain excessively discharges the condition, for prevented excessively discharges the occurrence, the battery should maintain the certain electric quantity.

7.5 Storing the Batteries

The battery should store in the product specification book stipulation temperature range. If has surpasses above for six months the long time storage, suggested you should carry on additional charge to the battery.

8. Period of Warranty

The period of warranty is 12 months from the date of shipment. Guarantees to give a replacement in case of cells with defects proven due to manufacturing process instead of the customer's abuse and misuse.

9. Other- The Chemical Reaction

Because batteries utilize a chemical reaction, battery performance will deteriorate over time even if stored for a long period of time without being used. In addition, if the various usage conditions such as charge, discharge, ambient temperature, etc. are not maintained within the specified ranges the life expectancy of the battery may be shortened or the device in which the battery is used may be damaged

by electrolyte leakage. If the batteries cannot maintain a charge for long periods of time, even when they are charged correctly, this may indicate it is time to change the battery.

10. Note

Any other items which are not covered in this specification shall be agreed by both parties.

End of Document.